



CR Classic* Face Mask with Earloops Gamma Sterilized Catalog # 62470-10

From Kimberly-Clark's World Class collection of face masks, the CR Classic* Face Mask with Earloops, Gamma Sterilized is a sterile, pleated mask used in class 100 and more critical environments¹. The mask is manufactured in facilities that meet the quality system requirements of ISO 9001:2000. Additionally, the products are packaged in facilities certified to satisfy the air cleanliness requirements of ISO Class 8 environments as defined by ISO 14644-1:1999 (E) entitled "Cleanrooms and associated controlled environments - Part 1: Classification of air cleanliness."

Each batch of product is sterilized following the universally recognized standard: ANSI/AAMI/ISO 11137, "American National Standard, Sterilization of Healthcare Products—Requirements for Validation and Routine Control—Radiation Sterilization." These products are sterilized to substantiate an Sterility Assurance Level of 10^{-6} .

- | | |
|-------------------------------|---|
| 1. Bindings | White Hydroentangled Polyester |
| 2. Nosepiece | Fully Enclosed, Soft, Malleable Aluminum |
| 3. Outer Facing | Clear, Polyethylene Apertured Film |
| 4. Inner Facing | White, Bicosof™ Fabric |
| 5. Filter Media | White, Meltblown Polyester |
| 6. Earloops | White, Tubular Knitted Polyester |
| 7. Mask Width | 7 inches wide |
| 8. Certificate of Irradiation | Attached to the case and also available on the website:
www.kcsafety.com |
| 9. Packaging | 20 Individually packaged masks per bag/10 Bags per case (200 masks per case) |
| 10. Construction | Ultra Sonic Bonding |

Particle Filtration Efficiency @ 0.1 micron, Post-Sterilization	86%²
Bacterial Filtration Efficiency # 3.0 microns, Post- Sterilization	94%³
Differential Pressure in mm H₂O @ 8 LPM flow rate, Post-Sterilization	2.12

For Further Information Contact: 1-800-255-6401
www.kc-safety.com

¹ Statement based on sales of products into fabs. We recommend testing the product for use in your facility.

² Testing based on ASTM F1215-89 was completed by an independent facility on 11 samples of product

³ Testing based on MIL-M-36954C was completed by an independent facility on 11 samples of product